

TECHNICAL CHARACTERISTICS

PURLINE | wineo 1200 to click (Semi-Rigid)

Permanently elastic polyurethane flooring according to EN 16776
Without the addition of chlorin, without plasticisers or solvents.

wineo

	wineo 1200 wood XL V4	wineo 1200 stone XL
Format	1507 x 246 mm	1000 x 500 mm
Product thickness	5 mm	5 mm
Weight	9 kg/m ²	9 kg/m ²
Profile connection	Fold-Down 	LocTec 
Planks / m² per box	6 / 2.22 m ²	6 / 3.00 m ²
Boxes / m² per pallet	48 / 106.56 m ²	36 / 108.00 m ²
Guarantee	You can find our guarantee conditions at – www.wineo.de	




Classification		Product composition	
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage	1
	Utilization class 33 EN ISO 10874	Commercial sector with heavy usage	
	Scratch resistance EN 16776, annex A	Utilization class 33: ≥ 6 N	
	R9 Anti slip category DIN 51130	R 9	2
	Staining and chemical resistance EN ISO 26987	Very good resistance according to the concentration and residence time	
	Light fastness EN ISO 105-B02	~ 7	3
	Residual indentation EN ISO 24343-1	≤ 0.10 mm	
	Effect of a furniture leg EN 424	in test: Foot type 2 – no visible change	4
	Castor chair test EN ISO 4918	25000 revolutions no damage with rolls type W	
	Thermal resistance ISO 8302	0.01 (m ² K)/W	
	Impact sound reduction EN ISO 10140	~ 5 dB	
	Dimension stability EN ISO 23999	≤ 0.15 %	
REACH		free from SVHC substances ≥ 0.1 %	
Disposal		Private: possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203	



www.blauer-engel.de/uz120



Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)



Relevant Information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperatur of 27 °C.
- Cleaning and care: See separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.