

wineo 600

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

wineo

	wineo 600 wood	wineo 600 wood XL	wineo 600 stone XL	
Format	1200 x 180 mm	1505 x 235 mm	914 x 457 mm	
Product thickness	2 mm	2 mm	2 mm	
Planks, tiles / m² per box	18 / 3.89 m²	12 / 4.24 m²	12 / 5.01 m²	
Boxes / m² per pallet	60 / 233.40 m²	64 / 271.36 m²	52 / 260.52 m²	
Guarantee	You can find our guarantee conditions at - www.wineo.de			
Classification				Product composition
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage		1 Surface seal
	Utilization class 32 EN ISO 10874	Commercial sector with average usage		2 Surface texture Various embossings
	Utilization class 41 EN ISO 10874	Light industry sector with moderate usage		3 Wear layer Thickness 0.4 mm
	Wear layer binder content EN ISO 10582	Typ I		4 Design Decor film
	R9 Anti slip category DIN 51130	R 9		5 Base layer
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time		6 Backing
	Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6		7 Underlay material silentPLUS (available separately)
	Residual indentation EN ISO 24343-1	≤ 0,1 mm without underlay mat ~ 0.17 mm with silentPREMIUM		  emissionsgeprüft schadstoffgeprüft PREMIUM
	Castor chair test ISO 4918	25000 revolutions no damage with rolls type W		
	Thermal resistance EN 12667	≤ 0.011 (m²K)/W without underlay mat ≤ 0.021 (m²K)/W with silentPREMIUM or silentPLUS		
	Impact sound reduction EN ISO 16251-1	~ 4 dB ~ 17 dB with silentPLUS		
	Dimensional stability EN ISO 23999	≤ 0,15 %		
REACH		free from SVHC substances ≥ 0.1 %		
Disposal		<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		
 - 18 -  www.wineo.de ÉMISSIONS DANS L'AIR INTÉRIEUR*  Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)  factory made coated				

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 29° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.